


## LOW PRESSURE POLYURETHANE FOAM INFORMATION

<b>Description</b>	Low pressure, two-component spray polyurethane foam adhesive
<b>SPF</b>	Spray Polyurethane Foam
<b>Applications</b>	Designed to adhere to a variety of substrates and insulation board stock in both new and recover applications.
<b>Preparation for use</b>	Substrate must be clean, dry, firm, free of loose particles, and free of dust, grease and mold release agents. Protect surfaces not to be foamed. Read SDS, Operating Instructions, and Product Stewardship Guidelines. For additional information go to <a href="http://www.icpadhesives.com">www.icpadhesives.com</a>
<b>Use</b>	Warm/Cool chemical to 70-85°F (21-29°C). Follow instructions for set-up found in the operating instructions.
<b>PPE</b>	 <p>Wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Recommend dispensing product in a well-ventilated area with certified respiratory protection; however, well ventilated exterior applications may not need respiratory protection. It is the responsibility of the employer to complete a PPE evaluation and/or exposure assessment to determine if respiratory protection is required. Read all instructions, ICP Product Stewardship Guidelines, and SDS (Section 8) prior to use of any product.</p>
<b>Note</b>	FOR PROFESSIONAL USE ONLY. Always check the local building code before use. Cured low pressure polyurethane foam is non-toxic and inert.
<b>Temperature</b>	Please see chart located on page 2. Lower substrate application temperatures will increase gel and tack free times. The applicator can also expect a slower rise time.
<b>Product Storage</b>	Store in a dry area. Optimum chemical storage temperature is 60-90°F (16-32°C). Excessive heat can cause premature aging of components resulting in a shorter shelf-life. Do not allow material to freeze.
<b>Disposal</b>	Refer to SDS (Section 13) for instructions. Always dispose of empty cylinders in according to applicable federal, state, provincial and local regulations.
<b>Shelf-life</b>	12 months
<b>Compatibility</b>	Cured low pressure polyurethane foam is chemically inert and non-reactive in approved applications. See compatibility chart located on page 2.
<b>Limitations</b>	Do not use when ambient substrate temperatures are below 40°F (4°C). Do not use during inclement weather, on wet surfaces or on any roof deck showing signs of deterioration or loss of structural integrity. Do not use after the expiration date. Do not use on insulating board stock larger than 4 x 4 ft.

TECHNICAL DATA	STANDARD	RESULTS
<b>Tensile Strength</b>	ASTM D412	23 psi
<b>Elongation</b>	ASTM D412	7.95%
<b>Peel Strength</b>	ASTM D903	23.5 lbf/in
<b>Water Absorption</b>	ASTM D471	2.5%
<b>Flexibility</b>	ASTM D816	Pass
<b>Fire Rating at 2.5" Thickness</b>	ASTM E84	Flame Spread Index 15 Smoke Developed 135

## TIME BEFORE WALKING IN

Ambient / Deck Temperature	Time
40-60°F (4-16°C)	6 – 10 minutes
60-80°F (16-38°C)	3 – 6 minutes
80-100°F (27-38°C)	1 – 3 minutes

## APPROVALS/STANDARDS/CLASSIFICATIONS

**UL - Underwriters Laboratories-** R20817 Testing in accordance with UL1897  
**FM - Factory Mutual** - Testing in accordance with FM Approval Class 4470.  
**Miami Dade NOA** - 16-0315.02  
**FBC - Florida Product Approval** - FL1365-R7



## PROPERTIES\*

<b>Open Time</b>	1 – 10 minutes
<b>Mixing Nozzle Working Time</b>	30 seconds
<b>Set-up Time (Tack Free)</b>	10 – 20 minutes
<b>Cure Time</b>	24 hours
<b>VOC Content (EPA Method 24)</b>	107 g/L

\*Times may be affected by temperature and weather conditions

## TEMPERATURE GUIDELINES

<b>Chemical Storage Temperature</b>	60-90°F (16-32°C)
<b>Outside Application Temperature/Ambient</b>	40-100°F (4-38°C)
<b>Process Core Chemical Temperature</b>	70-85°F (21-29°C)
<b>Surface Temperature (Substrate/Deck)</b>	40-100°F (4-38°C)
<b>Cured Foam</b>	-200°F to +240°F (-129°C to +116°C)

## YIELD\* AND WEIGHT

Product Number	Spatter Pattern 1/4" to 1/2" nominal thickness	2.5" bead, 12" OC	Net Weight
<b>62496580302</b>	2000 ft <sup>2</sup> (185.8 m <sup>2</sup> )	1800 – 2000 ft <sup>2</sup> (167.2 - 185.8 m <sup>2</sup> )	40 lbs (18.1 kg) A-Side; 35 lbs (15.8 kg) B-Side
<b>62000180302</b>	600 ft <sup>2</sup> (55.7 m <sup>2</sup> )	400 – 600 ft <sup>2</sup> (37.1 – 55.7 m <sup>2</sup> )	36 lbs (16.3 kg) / Kit
<b>62000380312</b> <b>Cold Weather</b>	2000 ft <sup>2</sup> (185.8 m <sup>2</sup> )	1800 – 2000 ft <sup>2</sup> (167.2 - 185.8 m <sup>2</sup> )	40 lbs (18.1 kg) A-Side; 35 lbs (15.8 kg) B-Side

\*Coverage rates may vary based on ambient temperature and application

## COMPATIBLE ROOF DECKS AND SUBSTRATES

Structural Concrete	Polyisocyanurate (flat or tapered)
Asphalt Primed Concrete	Extruded or Expanded Polystyrene
Pre-cast Concrete	High density wood fiber
Various BUR (smooth or gravel)	Gypsum boards
Base Sheets	Cement roof boards
Steel-22 gauge or lower with approved cross section	
Lightweight Structural Concrete	
Cementitious Wood Fiber Planks	
Insulating Concrete	
Vapor Retarders (hot, cold, torch-applied)	
Gypsum	

## COMPATIBLE ROOF INSULATIONS AND COVER BOARDS

**Always read all operating, application and safety instructions before using any products.** Use in conformance with all local, state and federal regulations and safety requirements. Failure to strictly adhere to any recommended procedures and reasonable safety precautions shall release ICP Adhesives & Sealants, Inc. of all liability with respect to the materials or the use thereof. For additional information and location of your nearest distributor, call ICP Adhesives & Sealants Inc. 1 330.753.4585 or 1 800.321.5585.

**NOTE:** Physical properties shown are typical and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions and may vary upon use, temperature and ambient conditions. Right to change physical properties as a result of technical progress is reserved. This information supersedes all previously published data. The Customer is responsible for deciding whether products and associated TDS information are appropriate for customer's use.

ICP low pressure one-component polyurethane foam sealants and adhesives (OCF), low pressure spray polyurethane foams (SPF), and low pressure pour-in-place polyurethane foams (PIP) are composed of a diisocyanate, hydrofluorocarbon or hydrocarbon blowing agent, and polyol. For polyurethane foam sealants/adhesives: wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Recommend using in a well-ventilated area. Avoid breathing vapors. Read the SDS and instructions carefully before use ([www.icpadhesives.com](http://www.icpadhesives.com)). For spray polyurethane foams and pour-in-place polyurethane foams: wear protective glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure. Use only in a well-ventilated area and with certified respiratory protection or a powered air purifying respirator (PAPR). Additional information on ventilation can be found in the Product Stewardship Guide ([www.icpadhesives.com](http://www.icpadhesives.com)). Read the SDS ([www.icpadhesives.com](http://www.icpadhesives.com)) and instructions carefully before use. The urethane foam produced from these ingredients will support combustion and may present a fire hazard if exposed to a fire or excessive heat about 240°F (116°C). Refer to each product's TDS for specifications, testing results, and other attributes. The customer is ultimately responsible for deciding whether products and associated TDS information are appropriate for customer's use. Refer to the products' SDS, ICP Adhesives & Sealants' Product Stewardship Guidelines, and operating instructions for guidance on the safe and proper application of the product ([www.icpadhesives.com](http://www.icpadhesives.com)). For professional use only. Building practices unrelated to materials can lead to potential mold issues. Material suppliers cannot provide assurance that mold will not develop in any specific system.

**WARNINGS:** Follow safety precautions and wear protective equipment as recommended. Prolonged inhalation exposure may cause respiratory irritation/sensitization and/or reduce pulmonary function in susceptible individuals. Onset may be delayed. Pre-existing respiratory conditions may be aggravated. We recommend that the product is used in a well-ventilated area and with certified respiratory protection. NIOSH approved positive pressure supplied air respirator is recommended if exposure guidelines may be exceeded. Contents may be very sticky and irritating to skin and eyes, therefore wear safety glasses with side shields or goggles, nitrile gloves, and clothing that protects against dermal exposure when operating. If liquid chemical comes in contact with skin, first wipe thoroughly with dry cloth, then rinse affected area with water. Wash with soap and water afterwards, and apply hand lotion if desired. If liquid comes in contact with eyes, immediately flush with large volume of clean water for at least 15 minutes and get medical help at once. If liquid is swallowed, get immediate medical attention. Do not induce vomiting. If breathing is difficult, give oxygen. If breathing has stopped give artificial respiration. Products manufactured or produced from these chemicals are organic and, therefore, combustible. Each user of any product should carefully determine whether there is a potential fire hazard associated with such product in a specific usage. **KEEP OUT OF REACH OF CHILDREN.**

**LIMITED WARRANTY and LIMITATION OF DAMAGES:** ICP Adhesives & Sealants, Inc. warrants only that the product shall meet ICP Adhesives & Sealants, Inc. specifications for the product when shipped by ICP Adhesives & Sealants, Inc. NO OTHER EXPRESSED OR IMPLIED WARRANTIES APPLY AND ANY IMPLIED WARRANTIES OF MERCHANTABILITY, NON-INFRINGEMENT OUTSIDE THE U.S. AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY DISCLAIMED. Buyer and users assume all risks of use, handling and storage of the product. Failure to strictly adhere to any recommended procedures shall release ICP Adhesives & Sealants, Inc. from all liability. The user of the product is responsible to determine suitability of the product for the particular use. The exclusive remedy as to any breach of warranty, negligence or other claim is limited to the replacement of the product. Liability for any indirect, incidental or consequential damage or loss is specifically excluded.



2775 Barber Road | Norton, OH 44203  
330-753-4585 | [icpadhesives.com](http://icpadhesives.com)

**MADE IN USA**  
WITH GLOBALLY SOURCED MATERIALS